

AMENDMENTS TO THE CLAIMS

This listing of claims will replace all prior versions and listings of claims in the application:

LISTING OF CLAIMS:

1. (previously presented): A glass paste comprising a magnesium titanate powder and a glass powder having a lower glass transition temperature than said magnesium titanate powder and having a glass transition temperature of 500°C or less, wherein the magnesium titanate powder has a refractive index of 2.0 or more, a reflective index at wavelengths of light of 400 nm, 550 nm and 700 nm in a light reflection spectrum of 80% or more, a primary particle size measured by scanning electron microscopy of from 0.1 μm to 10 μm , and a BET specific surface area of from 0.1 m^2/g to 15 m^2/g .

2. (previously presented): A glass paste comprising a magnesium titanate powder and a glass powder having a lower glass transition temperature than said magnesium titanate powder and having a glass transition temperature of 500°C or less, wherein the magnesium titanate powder has a refractive index of 2.0 or more, a reflective index at wavelengths of light of 400 nm, 550 nm and 700 nm in a light reflection spectrum of 80% or more, a primary particle size measured by scanning electron microscopy of from 0.1 μm to 10 μm , and a BET specific surface area of from 0.1 m^2/g to 10 m^2/g .

3. (previously presented): The glass paste according to Claim 1, wherein a ratio of the primary particle size by scanning electron microscopy of the magnesium titanate powder to a primary particle size calculated from the BET specific surface area is from 0.1 to 5.

4. (previously presented): The glass paste according to Claim 2, wherein a ratio of the primary particle size by scanning electron microscopy of the magnesium titanate powder to a primary particle size calculated from the BET specific surface area is from 0.1 to 5.

5. (previously presented): The glass paste according to Claim 1, wherein the magnesium titanate powder comprises a polyhedral particle having substantially no fractured surface.

6. (previously presented): The glass paste according to Claim 2, wherein the magnesium titanate powder comprises a polyhedral particle having substantially no fractured surface.

7. (canceled).

8. (canceled).

9. (currently amended): A glass paste obtained by mixing an organic substance into a composition obtained by compounding a magnesium titanate powder according to Claim 1 in an amount of 1% by weight to 80% by weight with a glass powder ~~having lower glass transition temperature~~ having a glass transition temperature of 500°C or less.

10. (currently amended): A glass paste obtained by mixing an organic substance into a composition obtained by compounding a magnesium titanate powder according to Claim 2 in

an amount of 1% by weight to 80% by weight with a glass powder ~~having lower glass transition~~
~~temperature~~ having a glass transition temperature of 500°C or less.